Mint of the United States at Philadelphia, Pa., ASSAY DEPARTMENT. November 16⁴, 1889. I number of experiments were made in this Office some gears since to ascertain the depreciation in value of Gold and Silver Coin by abrasion: We found that a lot of double eagles whose average age was 6 years, showed an annuel lors of 11.3 cents on \$100a-Eagles whose average age was 11 years 21,5 cents on \$1000. – Half Eagles average age 12 years 28.2 cents on \$1000. - Laarter eagles average age 10 years 37.6 cents on \$1000. Of course the weight after washing, was The weight taken, as it indicates the real loss by wear, by comparison with the lawful weight of new X clean coins.

These experiments were made previous to the

Mint of the United States at Philadelphia, Pa.,

ASSAY DEPARTMENT,

18

war, when Gold was largely in circulation there being no United States notes.

From experiments just lately made, we have found that a lot of half eagles whose ages were seven & nine years, showed an annual loss of 21 cents on \$1000.

Jacob BEckfelat Awayen

U.S. Treasury Department.

Mint of the United States at Philadelphia, Pa., Assay Department, November 16, 1889

A number of experiments were made in this office some years since to ascertain the depreciation in value of gold and silver coin by abrasion.

We found that a lot of double eagles whose average age was 6 years, showed an annual loss of 11.3 cents on \$1000.

Eagles whose average age was 11 years 21.5 cents on \$1000. Half Eagles average age 12 years 28.2 cents on \$1000. Quarter eagles average age 10 years 37.6 cents on \$1000.

Of course the weight after washing was the weight taken, as it indicates the real loss by wear, by comparison with the lawful weight of new & clean coins.

These experiments were made previous to the war, when gold was largely in circulation there being no United States notes.

From experiments just lately made, we have found that a lot of half eagles whose ages were seven & nine years, showed an annual loss of 21 cents on \$1000.

Jacob B. Eckfeldt Assayer

[Enclosed note:]

U.S. Treasury Department

Gold

Fineness	1792	.916 2/3
"	1834	.899.225
"	1837	.900

Silver

"	1792	892.4
"	1837	900.